

MODERDIRECT SUPRA

	Yellow PG		Yellow RL		Orange ZGL		Scarlet F2G		Scarlet 3BSL		Red ME		Red BWS		Red 4B		Rose FR		Rubrine BL	
	non	Fix	non	Fix	non	Fix	non	Fix	non	Fix	non	Fix	non	Fix	non	Fix	non	Fix	non	Fix
Dyeing depth (%o.w.f.)	2		2		2		2		2		2		2		2		2		2	
Solubility (80°C.g/l)	50		80		100		40		25		100		100		80		100		70	
S.D.C. Classification	B		B		B		B		C		B		B		B		B		B	
Optimum affinity Temp. °C	60-70		90		80		90		80-100		80		80		80		90		100	
Suitability for High Temp. dyeing	C		C		C		C		C		B		B		B		A		B	
Fastness to Light	4-5		5		6-7		3-4		2-3		4-5		4-5		4		3		7-8	
	4-5		5		4		3-4		3		3		3		3		3		5	
	3-4		4		4		3		4		5		4-5		4-5		3-4		4-5	
Fastness to washing ISO 105-C02	3		3		2		1		1-2		2		3		3		1		1	
	6		5		4-5		4		4-5		4		4-5		5		4-5		3	
	3-4		4-5		4		4-5		4-5		4		5		5		4-5		4	
Fastness to water ISO 105-E01	2-3		5		2-3		5		3		4-5		1-2		5		2-3		4-5	
	4-6		5		4		5		3-4		4-5		5		5		4-5		3	
	3		4		3-4		3-4		2		2-3		3		3-4		2-3		1-2	
Fastness to perspiration ISO 105-E04 (Acid)	4-6		5		4-5		4		4-5		4-5		4-5		4-5		4-5		4	
	4		4-5		5		3-4		4		5		5		5		5		5	
	4-5		4-5		5		4-5		4		4		5		5		5		5	
Fastness to rubbing ISO 105-X12	3		4		3-4		2		2-3		3		3-4		3		2-3		1-2	
	4-5		4-5		4-5		3-4		4-5		4-5		4-5		4-5		4		4	
	4-5		4-5		4		4-5		4		4-5		4-5		4-5		4		4-5	
Staining on Multi-Fiber (0.5% o.w.f.)	1		2		1		2		2		2		2		2		2		2-3	
	2-3		4-5		2-3		2		2		2		2		2		2		1-2	
	1		1		1		1		1		1		1		1		1		1	
Polyester	3		4		2-3		2		2		1-2		1-2		1-2		2		2	
	4-5		4-5		4-5		4-5		2-3		4-5		4-5		4-5		4-5		4-5	
	4-5		4-5		4-5		4-5		2-3		4-5		4-5		4-5		4-5		4-5	

*Remark: Blue BRL is banned amine